



City Cat House, 29, Police Court Lane, Fort, G.P.O. Box No. 1343, Mumbai – 400 001. (India)  
 Tel.: 00-91-22-2265 1703 / 2265 1704 / 2262 2443 · Fax: 00-91-22-2263 0348 / 2265 0815 / 2265 7891.  
 E-mail: [citycat@vsnl.com](mailto:citycat@vsnl.com) · [info@citycatpigments.com](mailto:info@citycatpigments.com) · Website: <http://www.citycatpigments.com>.

## Zinc Stearate

<b>Properties</b>	<b>Unit</b>	<b>Cataflow (001)</b>	<b>Cataflow (002)</b>	<b>Cataflow (003)</b>
Bulk Density	gm/cc	0.09	0.22-0.25	0.38
Electrolytes	% max	1.0	1.0	0.1
Moisture	% max	1.0	1.0	0.3
pH of 2% aqueous slurry	--	6.5 – 7.5	6.5 – 7.5	6.5 – 7.5
Ash Content	%	13.5 – 14.5	13.5 – 14.5	13.5 – 14.5
Zno Equivalent	% as	13.0 – 14.0	13.0 – 14.0	13.0 – 14.0
Melting Point	° C	118 - 121	118 - 121	118 - 121
Melt Quality	--	Clear Transparent	Clear Transparent	Clear Transparent
Colour	--	White	White	White
Foreign Particles	--	Comparable to standard	Comparable to standard	Comparable to standard
Free Fatty Matter	% max	0.5	1.0	2.0
Residue on 240 mesh	% max	0.04	0.5	0.5